ChemStar Mechanical Packing, Inc.

Address: 3010 Reynolds Rd

Lakeland, FL 33803 USA

Office: (863) 425-5581 / (800) 397-5581

Fax: (863) 425-5762

Email: sales@chemstarpacking.com Website: www.chemstarpacking.com



STYLE 3165



- Temperature: To 550°F / 285°C
- pH Range: 0-14
- Speed: 4500 FPM
- Pressure: 300 PSI / 20
 - Bar
- Construction: Interlock

Braid

Description: A special blend of graphite filled PTFE fiber with

excellent thermal conductivity, chemical and abrasive resistance. 3165 is flexible and pliable and will not

harden, swell or become brittle.

Equipment: Any type of pump-centrifugal, rotary, turbine, and

reciprocating. It can also be used in valves, agitators,

mixers, dryers and refiners.

Applications: Solvents, chemicals, gases, corrosives, water, steam,

slurries, paper stock, black liquor, oils and ammonia

Industries: Chemical & Pharmaceutical, Agriculture, Pulp & Paper,

Marine, Oil & Gas, Steel, Power generation, Municipal/

Wastewater and General industry